

Magic Power Gel

Gel: UL 94-HB

Dielectric strength:
>23 kV/mm

Cross linking time:
fast (about 15 min. at 25°C)

Volume resistivity:
>2 · 10¹⁵ Ω cm

Operating temperature:
-60°C / +200°C

**Overload temperature
for short periods:**
up to 250°C

Stabilised for:
mould - UV

Degree of protection:
IP68 (in proper casings)

IP68
OFFICIALLY
TESTED | **IMQ**

Nonfood
Compounds
P1



INSULATING and SEALING GEL

RE-ENTERABLE

RE-USABLE

The unique bi-component gel in a single bottle, with superior dielectric, sealing and thermal characteristics, re-enterable and re-usable!

- Very sticky
- Strong self amalgamating characteristics
- Single compact bottle; convenient twin compartment
- Re-usable as well as re-enterable, even after long working periods
- It doesn't give any waste
- The gel is not-classified as hazardous under the CLP Directive





Stickiness

- Exceptional sealing properties in any condition
- Better resistance to pressure
- Effective even in vertical or ceiling applications

Self-agglomerating

- Once cross linked it perfectly adheres on itself characteristics to get an homogeneous and compact mass
- It can be therefore applied in multiple layers

Zero waste

- Due to the nature of the product waste is eliminated; even residual product can be saved and used for the next application
- Also any left over product maintains it's high performance characteristics

Single bottle

- Highly useful
- The most compact packaging
- Less space occupied in the toolbox
- Both components in the same packaging



For all types of connections, even in the toughest conditions, for power, telecom and signalling!

Product	Colour	Package type	Quantity
Magic Power Gel	●	1 single, bi-component bottle 1 small basin - 1 mixing spoon	1000 ml
Magic Power Gel 500	●	1 single, bi-component bottle 1 small basin - 1 mixing spoon	500 ml
Magic Power Gel 250	●	1 single, bi-component bottle	250 ml
Magic Power Gel Bag 150	●	Bicomponent single dose bag	150 ml
Magic Power Gel Bag 250	●	Bicomponent single dose bag	250 ml

